MICROMETALS™
POWDER CORE SOLUTIONS

Part Number:	T44-2

Revision 20190524 - Generated 2019-May-30



OD	(nom. - bare core)	11.18 mm	0.440 in
	(max. - after coating)	11.68 mm	0.460 in
ID	(nom. - bare core)	5.82 mm	0.229 in
	(min. - after coating)	5.31 mm	0.209 in
Ht	(nom. - bare core)	4.04 mm	0.159 in
	(max. - after coating)	4.55 mm	0.179 in
Mass	(approximate)	1.3 grams	
Magnetic Dimensions	A_e - Eff. Mag. Cross Section	0.0990 cm²	
	L_e - Eff. Mag. Path Length	2.68 cm	
	V_e - Eff. Core Volume	0.266 cm³	
	WA - Min. Eff. Window Area	0.221 cm²	
	sa - Surface Area	4.81 cm²	
	mlt - mean length per turn	1.81 cm	
Inductance	μ_i(reference)	10	
	A_L value (nominal)	5.2 nH/N²	
	Test Winding	N=100, #34 AWG	
	Frequency	1 MHz	
	Voltage on Agilent 4284A	1.0 V	
	A_L tolerance	±5%	
Core Loss & Q	Core Loss(mW/cm³)= $\frac{f}{\frac{a}{Bpk^{3}}+\frac{b}{Bpk^{2.3}}+\frac{c}{Bpk^{1.65}}}+d\cdot Bpk^{2}\cdot f^{2}$		
	where B_{pk} expressed in gauss, f expressed in hertz, and:		
	a=4.00E+09, b=3.00E+08, c=2.70E+06, d=9.60E-16		
	Q test winding	N=100, #34 AWG	
	Q frequency	2 MHz	
	Q min on HP4342A	137	
DC Saturation	$\%\mu_i = \frac{1}{a+b\cdot H^{c}}+d$		
	where H expressed in oersteds, and:		
	a=1.00E-02, b=1.83E-07, c=1.46, d=0.00		
	H_{DC}	200 Oe	
	Percent Initial Perm(nom.)	95.9%	
	Percent Initial Perm(min.)	94.8%	
Coating/Pkg	Coating Type:	Red/Clear Epoxy Paint	
	Voltage Breakdown (min.)	500 Vrms, 60Hz	
	Limit	3 mA, 5 s	
	Package Quantity	10,000 Pcs/Box	









Winding Table	**Wire Size**	AWG	18	20	22	24	26	28	30	32	34	36	38
		mm	1.000	0.800	0.630	0.500	0.400	0.315	0.250	0.200	0.160	0.125	0.100
	Single Layer	Turns	11	14	18	23	29	37	47	59	74	93	116
		Rdc(Ω)	4.2 m	8.4 m	17.3 m	35.1 m	70.3 m	142.7 m	288.3 m	575.7 m	1.1	2.3	4.6
	Full Winding	Turns	10	16	25	38	59	91	141	219	339	524	812
		Rdc(Ω)	3.8 m	9.6 m	24.0 m	58.0 m	143.1 m	351.0 m	865.0 m	2.1	5.3	12.9	31.9

Micrometals Iron Powder Cores, A Division of Micrometals, Inc. - 5615 E. La Palma Ave., Anaheim, California 92807 USA
Ph: +1-714-970-9400, Toll Free in USA: +1-800-356-5977
www.Micrometals.com