



Part Number: **T106-0**

Revision 20190524 - Generated 2019-May-30



OD	(nom. - bare core) (max. - after coating)	26.92 mm 27.43 mm	1.060 in 1.080 in
ID	(nom. - bare core) (min. - after coating)	14.48 mm 13.97 mm	0.570 in 0.550 in
Ht	(nom. - bare core) (max. - after coating)	11.10 mm 11.73 mm	0.437 in 0.462 in
Mass	(approximate)	9.4 grams	
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	0.659 cm ²	
	L _e - Eff. Mag. Path Length	6.49 cm	
	V _e - Eff. Core Volume	4.28 cm ³	
	WA - Min. Eff. Window Area	1.53 cm ²	
	sa - Surface Area	28.1 cm ²	
	mlt - mean length per turn	4.39 cm	
Inductance	μ _i (reference)	1	
	A _L value (nominal)	1.9 nH/N ²	
	Test Winding	N/A	
	Frequency	N/A	
	Voltage on Agilent 4284A	N/A	
A _L tolerance	Ref Only		
Core Loss	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{Bpk^3} + \frac{b}{Bpk^{2.3}} + \frac{c}{Bpk^{1.65}}} + d \cdot Bpk^2 \cdot f^2$		
	where B _{pk} expressed in gauss, f expressed in hertz, and: a=1.00E+99, b=1.00E+99, c=1.00E+99, d=0.00E+00		
	Bpk	140 G	
	frequency	100 kHz	
	Core Loss (nominal)	0 mW/cm ³	
Core Loss (maximum)	0 mW/cm ³		
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$		
	where H expressed in oersteds, and: a=1.00E-02, b=0.00E+00, c=0.00, d=0.00		
	H _{DC}	200 Oe	
	Percent Initial Perm(nom.)	100.0%	
Percent Initial Perm(min.)	100.0%		
Coating/Pkg	Coating Type:	Tan/Tan Epoxy Paint	
	Voltage Breakdown (min.)	500 Vrms, 60Hz	
	Limit	3 mA, 5 s	
	Package Quantity	700 Pcs/Box	

Winding Table	Wire Size	AWG	10	12	14	16	18	20	22	24	26	28	30
		mm	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315	0.250
	Single Layer	Turns	12	15	20	26	32	41	52	65	82	102	128
		Rdc(Ω)	1.7 m	3.4 m	7.3 m	15.0 m	29.4 m	59.9 m	120.8 m	240.2 m	482.0 m	953.5 m	1.9
Full Winding	Turns	12	19	30	46	71	110	171	264	409	633	980	
	Rdc(Ω)	1.7 m	4.3 m	10.9 m	26.6 m	65.2 m	160.7 m	397.4 m	975.7 m	2.4	5.9	14.6	

